







# **PALRUF**® Corrugated PVC Sheet







# Content

About Palram	2
PALRUF® - For the Long Term	3
Main Benefits of PALRUF®	4
PALRUF® Project Gallery	6
Colors	12
Physical Properties	13
Flammability, Building and Construction Standards	14
Weather Resistance	14
Resistance to UV Radiation	15
Chemical Resistance	15
Standard Profiles	16

1

### **About Palram**

#### A Global Leader in Thermoplastic Panels

Established 50 years ago, Palram has grown into a leading global manufacturer of semi-finished extruded thermoplastic sheets, panel systems and finished products. Palram sheets, manufactured mainly from polycarbonate and PVC, are designed to suit a diverse range of applications in various markets, which include DIY, construction, architectural projects, advertising, agricultural, glazing, and fabrication. Palram panel systems are offered as part of the company's advanced products and services bundle for the construction and architectural markets. A variety of consumer products are marketed through DIY chain stores across the globe.

Palram delivers excellence to a global marketplace, backed by professional support and service on both local and regional levels.

Palram is proud of its unique corporate culture that makes us agile, creative and committed to all our customers.

#### **Research and Development**

Palram pioneered the extrusion of PVC panels and has relied on innovative product culture ever since. The company constantly adapts new technologies to improve its manufacturing methods and keeps track with market demands. This production expertise results in an evolving product range, which refines the company's ability to match the most suitable product to each project.

#### **Global Presence**

Palram operates production plants in Europe, the Americas and on the shores of the Mediterranean, allowing constant logistic support and supply of PALRUF sheets.



### PALRUF® - For the Long Term

PALRUF corrugated PVC panels combines excellent resistance to chemicals, fire and impact, resulting in an extremely durable roofing solution. PALRUF withstands harsh chemical environments where conventional roofing quickly corrodes, which makes it ideal for long-term use in demanding industrial applications such as chemical plants and storage facilities, mines and ports. For domestic applications, it is ideal as a clear (in cold northern climates) or opaque roofing material that is easy to install and maintain. PALRUF evolved into the high quality product it is today based on the experience of 50 years of service. It is lightweight, safe, extremely easy to handle and install using conventional tools and requires minimum maintenance.



### Main Benefits of PALRUF®





# PALRUF® Project Gallery

### Roofing and Cladding Applications in Chemically Agressive Environments

PALRUF prevails where alternative materials fail. It provides a long term solution for roofing and cladding in industrial environments and reduces overall maintenance work and expenditure.

- Chemical processing plants
- Pulp and paper production
- Pharmaceutical Plants
- Oil refineries
- Fertilizer plants
- Power stations
- Steel mills
- Mines
- Ports
- Metal refining & processing
- Conveyor roofing

**Project:** Coca Cola Plant - Middle East | **Type:** PALRUF® White 3mm



**Project:** Dead Sea Plants - Middle East | **Type:** White Opaque 2mm



Project: Dead Sea Plants - Middle East | Type: PALRUF® White Opaque 2mm



**Project:** TIS Port - Odessa, Ukraine | **Type:** PALRUF® 3mm White Opaque and Clear (Clear sheets used as skylights)



**Project:** Caserones Mine - Chile | **Type:** PALRUF® White Opaque 3mm



### **Livestock and Farming Applications**


PALRUF withstands aggressive chemical environment typical of livestock structures. It would make an ideal roofing, siding and internal cladding solution for a long service period.

- Poultry farms
- Pig farms
- Dairies
- Fish farms
- Barns
- Fertilizer warehouses

**Project:** Pig Farm - Middle East | **Type:** PALRUF® White Opaque 2mm



**Project:** Fish Research Farm - University of Maine, USA **Type:** PALRUF® White Opaque 3mm



Project: Unicoop Planta UPM Pig Breeding Farm - Paraguay (8,900sqm) | Type: PALRUF® Opaque White 3mm



**Project:** Dairy Farm - Canada | **Type:** PALRUF® White Opaque 3mm



**Project:** Dairy Farm - Middle East | **Type:** PALRUF® White Opaque 3mm



### Do It Yourself (DIY) Applications

PALRUF® is lightweight and extremely easy to handle and install around the house. The sheets will maintain their appearance with minimum maintenance and withstand extreme weather conditions for a long period.

- Pergolas
- Small warehouses
- Carports
- Canopies
- Patios

**Project:** Residential Carport - Middle East | **Type:** White 1mm




Project: Residential Pergola - Canada | Type: PALRUF® Clear 1mm



Project: Residential Pergola - Germany | Type: PALRUF® Clear 0.8mm



**Project:** Residential Pergola - USA | **Type:** PALRUF® Clear 0.8mm





### PALRUF® Colors

When specifying PALRUF colors, it is important to consider the climactic conditions where the sheets will be installed, as described in the table below. Opaque White PALRUF is suitable for any climate and geographical region and will serve as a cost effective roofing solution in most cases. PALRUF is also available in a range of transparent, translucent and other opaque colors, which should be specified according to the weather conditions in the area of installation: clear and standard colors are suitable for relatively cold climates, whereas special cool colors can be applied in warmer regions. For more details and professional consultation regarding color application please contact your Palram distributor.

# Colors

Group	Description	Colors
White Opaque	Ideal for any climatic conditions. Does not transmit light.	White Opaque
Opaque Colors	Suitable for most regions - please consult with your Palram distributor before specifying.  Does not transmit light.	Light Gray Beige
Special Cool Opaque	Suitable for any climatic conditions due to a unique feature that stabilizes the sheet's temperature.  Available with any color on special orders only, subject to a minimum order.	Light Blue Red Dark Green
Opal	Suitable for cold climates only. PALRUF Opal sheets transmit 20-40% of incident light.	White White Opal Diffuser Blue
Transparent	Suitable for cold climates only.  Transparent colors offer good light transmission and clarity, and can be either clear or tinted.	Clear Bronze

# **Physical Properties**

Property	Method*	Conditions	Units	Value
Density	D-792		g/cm³	1.4
Heat deflection temperature (H.D.T)	D-648	Load: 1.82 MP	°C	61 - 67
Service Temperature Range			°C	-20 to +50
Thermal conductivity	C-177		W/m K	0.16
Coefficient of linear thermal expansion	D-696		cm/cm°C	6.3 x 10 <sup>-5</sup>
Impact strength	ISO 6603/1	2 mm sheet	J	45 - 60
Tensile strength at yield	D-638	10 mm/min	MPa	50 - 66
Tensile strength at break	D-638	10 mm/min	MPa	39 - 53
Elongation at yield	D-638	10 mm/min	%	3
Elongation at break	D-638	10 mm/min	%	>80
Tensile modulus of elasticity	D-638	1 mm/min	MPa	2,900
Flexural strength	D-790	1.3 mm/min	MPa	90 - 100
Flexural modulus	D-790	1.3 mm/min	MPa	2,700
Rockwell hardness	D-785		R Scale	105 - 115

<sup>\*</sup> ASTM method except where noted otherwise.

Please consult your Palram distributor on the following:
■ Select the right color for your location and application ■ Receive a sample color chip ■ Order custom colors

### Flammability, Building and Construction Standards

PALRUF complies with stringent international building and construction standards shown in the table below.

Standard	Country	Method	PALRUF® Type	Designation or Rating
Cyclonic Test	Australia	AS2424	Industrial Profile	Passed
Flammability	Australia	AS1530-3		Conforms*
Flammability	France	NFP 92501, NFP 92505		M-1*
Flammability	Germany	DIN 4102		B-1*
Flammability	UK	BS 476/7		Class 1*
Flammability	USA	ASTM D-635		CC1*
Flammability	USA	ASTM E-84, D-3286, D-1929		Class 1*
Flammability	USA	Flame Spread Rating		12 – Class A*
Flammability	Israel	755		V 2 3*
Retention of Profile and Impact Resistance	Australia	AS2376-1980		Complies
ITB	Poland	AT-15-5324/2002		Approved
Static and Impact Tests	Australia	AS2424-91	American Industrial	Passed*
Windstorm Classification	UK	FMRC 4470 Approval Requirements		I-60 and I-90*

### Weather Resistance

PALRUF sheets retain their physical properties and attractive appearance despite exposure to various climactic conditions. They withstand humidity, rain and snow and provide weather protection over a large temperature range, from -20°C to 50°C (-4°F to 120°F). Proven weather resistance ensures the long-term flawless performance of PALRUF sheets.




### Resistance to UV Radiation

PALRUF® Opaque - Inherently protected by an internal UV absorber and offered in White, Light Grey and Beige colors.

PALRUF® Clear - UV stabilized sheet, recommended for use in regions where heat and the sun's radiation are limited.

**PALRUF® UV** - A protective layer on the outer side makes this sheet resistant to UV radiation and helps it retain its properties for many years. PALRUF UV is recommended for regions characterized with intense UV radiation.

**PALRUF® Clear UV** - UV stabilized sheet with protective layer on the outer side for outdoor use in any climate. This sheet will resist hard chemical environments and maintain its clarity far better than some alternatives, as seen in the graph below.



The graph above compares light transmission ratings of PALRUF Clear UV with fiberglass as a function of accelerated weathering (QUV exposure). After 1000 hours of QUV exposure, PALRUF Clear UV sheets retained their appearance and properties. The change in yellowness index was not detectable by the eye. QUV is an accelerated laboratory weathering test. 100 hours of QUV exposure are approximately equivalent to one year of outdoor exposure to solar UV radiation in regions with hot climates such the USA's Southwest, Australia and the Middle East.

#### Chemical Resistance

The mechanism of chemical attack on thermoplastics in general, and Palram PVC sheets in particular, differs significantly from the mechanism of corrosion of metals. Corrosion of metals results in a gradual loss of surface material as a result of electrolytic action by the relevant chemicals. Chemical attack on Palram PVC sheet, where it occurs, consists generally of absorption of the chemical by the PVC sheet and its subsequent swelling.

PALRUF corrugated pvc sheets provide exceptional resistance against the following classes of chemicals in both liquid and vapor form: mineral acids, alkalis plating solutions, paper making chemicals, pickling solutions, most inorganic compounds, alcohols aliphatic hydrocarbons, glycols, amines and phenols. PALRUF PVC sheets should not come into contact with acetone, ethers, esters or aromatic hydrocarbons.

A detailed chemical resistance list is available in the "Chemical Resistance of Palram PVC Sheets" file, available at your Palram distributor and the Palram international website.

Detailed information on sealants chemically compatible with PALRUF is available in the "Adhesives and Sealants for Palram PVC Sheets" list, which is available for download from the PVC product pages in all Palram websites.

# Standard Profiles\*

\*Custom designed profiles are available upon request, subject to a minimum order.

PALRUF®	Designation	Cover Width mm (Inch)	Standard Width mm (Inch)	Drawing
100	40/250	1000 (39.4″)	1063 (41.8″)	1063
2800	14/67.8	610 (24″)	660 (26″)	67.8
5100	DV4	1000 (39.4″)	1090 (42.9″)	333.3
6500	36.5/171.5	686 (27″)	756 (29.8″)	171.5 36.5 756
5,6 Wave	51/177	1062 (41.8") 1062 (41.8") 885 (34.8") 708 (27.9")	1170 (46") 1100 (43.3") 1020 (40.1") 920 (42.9")	1100
American 2.6"	20/68	949 (37.4″)	1020 (40″)	67.8
American 4.2"	27/107	1284 (50.6") 963 (37.9") 856 (33.7")	1390 (55″) 1070 (42.1″) 1017 (40″)	1070
Big 6	48/146	1025.8 (40.3″)	1086 (42.7″)	146.5
Big 6 IM Sunlux	38.8/146.5	1016 (40")	1086 (42.7″)	146.5
Astoria	38/305	915 (36″)	1025 (40.4")	305
B5 130/30	30/130	910 (35.8″)	1020 (40″)	130

 ${}^*\text{Custom}$  designed profiles are available upon request, subject to a minimum order.

PALRUF®	Designation	Cover Width mm (Inch)	Standard Width mm (Inch)	Drawing
Greca 70	18/70	1120 (44.1") 1120 (44.1") 1050 (41.3") 1050 (41.3") 700 (27.6") 490 (19.3")	1160 (45.5") 1140 (45") 1103 (43.4") 1090 (42.9") 765 (30.1") 550 (21.7")	18
Greca 70 Ond	18/70	1050 (41.3″)	1090 (42.9″)	18
Greca 75	20/75	1275 (50.2") 1200 (47.2") 1125 (44.3") 1050 (41.3") 600 (23.6") 600 (23.6")	1285 (51.6") 1274 (50") 1135 (44.7") 1060 (41.7") 642 (25.3") 637 (25")	32 1274 20
Greca 76	18/76	1140 (44.9") 1140 (44.9") 988 (38.9") 988 (38.9") 912 (35.9") 912 (35.9")	1190 (46.8") 1145 (45") 1060 (41.7") 1045 (41") 980 (38.5") 963 (38")	76 1190 ∞
Iron 76	18/76	1140 (44.9") 988 (38.9") 836 (32.9") 836 (32.9") 608 (23.9")	1150 (45.3") 1067 (42") 900 (35.4") 860 (33.8") 660 (26")	76
Mini	8/32	1024 (40.3") 732 (28.8") 640 (25.2")	1040 (41") 750 (30") 660 (26")	1040
3"	19/72	648 (25.5")	755 (29.7″)	72 19
7.2"	38.1/82.9 (1.5"/7.2")	1098 (43.2") 1098 (43.2") 915 (36") 915 (36")	1217 (47.9") 1150 (45.3") 967 (38.1") 965 (38")	965.2
9"	3/4" / 9"	914 (36″)	965 (37.8″)	228.6 (9") 961

All marketing materials and any content therewith provided by Palram® are provided solely for the purpose of supporting and enhancing the marketing of Palram® products. These materials are protected by Palram's intellectual property rights and may not be used for any other purpose or in connection with the sale of products of any other manufacturer. These materials may not be transferred to or used by any third party without prior permission of Palram.



#### PALRAM H.Q.

Tel: +972 4 8459900 Fax: +972 4 8444012 palram@palram.com www.palram.com

#### PALRAM EUROPE LTD.

Tel: +44 1302 380777 Fax: +44 1302 380788 sales.europe@palram.com www.palram.com

#### PALRAM AMERICAS

Tel: 610 2859918 Fax: 610 2859928 palramamericas@palram.com www.palramamericas.com



On.

In as much as Palram Industries has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own tests to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any Palram Industries patent covering such use or as recommendations for use of such materials in the infringement of any patent. Palram Industries or its distributors cannot be held responsible for any losses incurred through incorrect installation of the material. In accordance with our company policy of continual product development you are advised to check with your local Palram Industries supplier to ensure that you have obtained the most up to date information.

